



## REFRACTORY CEMENT A700

	ITEMS	SPECIFICATION (%)
<b>Chemical Compositions(%)</b>	Al <sub>2</sub> O <sub>3</sub>	50-60
	SiO <sub>2</sub>	8 Max
	Fe <sub>2</sub> O <sub>3</sub>	2.5 Max
	R <sub>2</sub> O	0.4 Max
<b>Fineness</b>	0.045mm sieve residue (%)	-
	Blaine specific surface (m <sup>2</sup> /kg)	-
<b>Physical Propertis(Time of setting)</b>	Initial setting time(h:min)	0:30 Min
	Final setting time(h:min)	6:00 Max
<b>Physical Propertis(Flexural strength)</b>	1d (MPa)	6.5 Min
	3d (MPa)	7.5 Min
<b>Physical Propertis(Compression strength)</b>	1d (MPa)	52 Min
	3d (MPa)	62 Min

PACKAGE: BIG BAG

All Size and Specifications are Available as Desired by Customer s